

# PRODUCT DATA



## STONDECK XD2 HD Interior Deck System - Heavy Traffic Areas



### DESCRIPTION

StonDeck XD2 is a semi-rigid solvent free polyurethane car park deck coating system which provides a colourful, crack bridging, waterproof wearing surface for high traffic indoor covered parking areas and is designed to meet requirements of CSA S413-07.

### USES / APPLICATIONS

StonDeck XD2 cosmetically enhances and reduces noise, provides lighter, safer environments to visit. StonDeck XD2 is suitable for refurbishment of existing decks and on new construction projects.

### BENEFITS

- Hard wearing – abrasion resistant
- Waterproof - Protects from chlorides
- Aesthetically attractive – brightens up dull, dark, musty car parks
- Reduces noise – stops tire squeal
- Solvent free
- Fire resistant
- Slip resistant
- Resistant to cracking
- Excellent bond strength

### MODEL SPECIFICATION

Product: StonDeck XD2 – Interior Deck Membrane  
Finish: Gloss  
Thickness: 50 mils

### SYSTEM COMPONENTS

#### StonDeck SF

A two-component, semi-flexible polyurethane bodycoat to hold the broadcast aggregate and provide system thickness.

#### StonDeck Aggregate\*

A high-wear graded quartz aggregate broadcast to provide an abrasion, slip and wear resistant surface.

\*System durability can be upgraded by substituting for emeraldum or aluminum oxide aggregates.

#### StonDeck Finish

A two component low viscosity and low flexibility sealer to seal the broadcast aggregate.

### ADDITIONAL COMPONENTS (If required):

#### StonDeck Primers

A range of two component, low viscosity epoxy primers to provide a strong, secure bond on damp and poor quality substrates.

### PHYSICAL CHARACTERISTICS

The figures that follow are typical properties achieved in laboratory tests at 20°C (68°F) and at 50% Relative Humidity.

|  |  |
|--|--|
| Slip Resistance<br>ASTM F1679                | Dry 1.20<br>Wet 0.95   |
| Temperature<br>Resistance                    | Softens over 70°C, hardens on cooling  |
| Water Permeability                           | Nil - Karsten test<br>(Impermeable)  |
| Chemical Resistance                          | Resistant to gasoline, oil, diesel, antifreeze, hydraulic fluid, chlorides and battery acids                                   |
| Resistance to<br>Chloride Ions<br>ASTM C1202 | Charge Passed <100 Coulombs.<br>Chloride Ion Penetration<br>Negligible   |
| Abrasion Resistance                          | Taber Abrader:<br>40 mg loss per 1000 cycles<br>(1 kg load using H-22 wheels)  |
| System Tensile<br>Strength<br>ASTM D412      | 7.15 N/mm <sup>2</sup> (1036 psi)  |
| System Elongation %<br>ASTM D412             | 50.9%  |
| Fire Resistance<br>BS476 Part 3<br>(2004)    | Designated EXT.F.AA<br>(Extended Fire Exposure<br>Roof Test)<br>- No fire penetration within<br>1 hour<br>- No spread of flame |
| Tear Strength<br>MOAT 27                     | Method 5.41<br>Test Result = 192 N (43 lbs.)   |
| Bond Strength<br>ASTM D4541                  | Greater than cohesive strength<br>of 3600 psi (25 N/mm <sup>2</sup> )<br>concrete >275 psi (1.9 MPa)                           |

Note: Complies with the requirements of ASTM C957.  
(Tests: ASTM C501, C794, C836, D412 and D471)

## SUBSTRATE REQUIREMENTS

Concrete substrate should be a minimum of 25 MPa, sound and free from laitance, dust, oils, and other contamination. Substrate should be dry to 80% Relative Humidity. (See Primers for damp/ poor substrates.)

## PACKAGING

StonDeck XD2 is conveniently packaged as detailed below for easy handling.

### StonDeck Primer (If required)

As required a range of Epoxy Primers for poor quality and damp substrates. See separate data sheets.

### StonDeck SF

3 gallon pail of Polyurethane Body Coat.  
(approx. 80 sq. ft. per. gallon at 20 mils.)

### Broadcast Aggregate

50 lb bags of quartz broadcast aggregate.\*  
(approx. 90 sq. ft./bag)

\*(Can be substituted with aluminum oxide or emeraldum for higher abrasion resistance)

### StonDeck Finish

3 gallon pail of StonDeck Finish Resin.  
(approx. 100 sq. ft./ gallon at 10 mils over texture)

## STORAGE CONDITIONS

Store all components between 60°F to 77°F / 16°C to 25°C in a dry area. Keep out of direct sunlight. Avoid excessive heat and do not freeze.

## COLOUR

StonDeck XD2 is available in 8 standard colours. Refer to the StonDeck colour sheet. Custom colours are available upon request with extended lead times.

## SPEED OF CURE

|                    | 10°C    | 20°C   | 30°C   |
|--------------------|---------|--------|--------|
| Light traffic      | 30 hrs  | 16 hrs | 10 hrs |
| Full traffic       | 36 hrs  | 24 hrs | 16 hrs |
| Full chemical cure | 12 days | 7 days | 5 days |

## CLEANING AND MAINTENANCE

For best performance clean regularly using a single or double rotary scrubber drier in conjunction with a mildly alkaline detergent.

## ENVIRONMENTAL CONSIDERATIONS

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless surface reduce the need for repairs, maintenance and cleaning. Environment and health considerations are controlled during manufacture and application of the products by StonCor staff and fully trained and experienced contractors.

## SUBSTRATE

Proper preparation is critical to ensure an adequate bond. The substrate must be dry and free of all wax, grease, oils fats, soil, loose or foreign materials and laitance. Laitance and unbonded cement particles must be removed by mechanical methods, i.e., abrasive blasting or scarifying. Other contaminants may be removed by scrubbing with a heavy-duty industrial detergent (Stonkleen TD9) and rinsing with clean water. The surface must show open pores throughout and have a sandpaper texture. For recommendations or additional information regarding a range of substrate priming and preparation options, contact StonCor's Technical Service Department.

## PRIMING (As required)

StonDeck Primers are available for poor quality and damp substrates when required. The primer must be fully cured and the concrete must be completely sealed off prior to the application of the membrane. For recommendations or additional information regarding substrate priming, contact StonCor's Technical Service Department.

## POT LIFE

After mixing, the StonDeck components will have a working time of approximately 10 – 15 minutes. The working time varies greatly depending upon temperature.

## BANDING

Proper banding of any cracks will ensure that the system is able to bridge dynamic cracking found in most parking decks and outdoor walkways. Application of the banding is accomplished as follows;

1. StonDeck Primer is mixed and applied immediately to the floor. It is applied using a nap roller to a width of 2" (50 mm) wider than the planned application of the membrane layer allow to cure.
2. StonDeck FD membrane is mixed and applied immediately to the primed floor using a brush to a thickness of approximately 30 mils (0.8 mm). Apply the banding to an approximate overall width of at least twice the slab depth at that location. Introduce localized reinforcement as required. Allow to cure.

## APPLYING

Application of the StonDeck system is accomplished as follows;

1. StonDeck Primer (if required) is mixed and applied immediately to the floor. The material is distributed using nap rollers. Allow to cure.
2. StonDeck SF is mixed and poured onto the floor. The material is distributed using notched trowel/squeegee and back rolled to ensure even distribution. After 5 minutes maximum, the chosen aggregate is broadcasted until refusal into the wet bodycoat. Allow to cure then remove excess aggregate.
3. StonDeck Finish is mixed and applied to seal the aggregate. The material is distributed using nap rollers. Ensure an even coat of approximately 8–10 mils is applied to fully seal the broadcast aggregate.

4. Refer to StonDeck XD2 Directions for further details.

#### RECOMMENDATIONS

- DO NOT attempt to install material if the StonDeck XD2 components are not within 60 to 77°F / 16 to 25°C
- DO NOT use water or steam in the vicinity of the application.
- The use of suitable protective clothing, gloves and safety glasses must be worn during mixing and application of the product.
- Avoid Contact! In case of contact with eyes, rinse immediately with copious amounts of water and seek medical attention. In case of contact with skin, clean immediately with water and soap.

#### NOTES

- Material Safety Data Sheets for StonDeck XD2 products are available upon request.
- A staff of Technical Service Engineers is available to assist with installation or to answer questions related to StonCor Decking products.
- Requests for technical service or literature can be made through local sales representatives and offices or corporate offices located worldwide.

**Important:**

StonCor believes the information contained here to be true and accurate as of the date of publication. StonCor makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

08/16



95 Sunray Street • Whitby, Ontario • L1N 9C9 • Tel: 800.263.3112 • Fax: 800.786.6329

Vancouver • Calgary • Edmonton • Regina • Saskatoon • Winnipeg • Toronto • Ottawa • Halifax  
Saint John • St. John's • Montreal • Gatineau • Québec • Sherbrooke • Trois-Rivières • Chicoutimi

[www.stoncorcpg.ca](http://www.stoncorcpg.ca)

#4499-08/16